



Tarpaulin Panamaflex Coated Media 900gsm

Items	Value	Unit	Test Method
Base Fabric	Polyester		
Yarn	1000x1000	D	
Construction	30x30	/sq.inch	
	12x12	/sq.cm	
Weight	900	g/sqm	
Weight Tolerance	6.6% difference		
Weight of Fabric	260	g/sqm	
Weight of PVC Coating	640	g/sqm	
Tensile Strength (L/W)	3900/3700	N/5cm	DIN53354 or HG/T2580
Tearing Strength (L/W)	535/480	N	DIN53363 or HG/T2581
Peeling Strength	50	N	DIN53357 or GB8808
Adhesion	90	N/5cm	DIN53357 or GB8808
Temperature Resistance	-30 ~ + 70	°C	DIN53361
Fire Rating	B2		
Material Warranty	6 Months		
UV Resistant	Yes		
Mildew Resistant	Yes		
Production Method	Use as tarpaulin, truck cover, awning, tentm inflatable product, geotextile.		
All above information shall only be used as a guide. Buyers shall independantly test and determine the products suitability			

Graphic Solutions Digital cc

Head Office
4 Midhurst Way
Constantia, 7806

Reg No. CK 1996/003463/23
Vat no. 494 015 4919
Tel: 021 794 6094