



Coated Fabric Wallpaper with Fire Resistance

TYPE	300E		
ITEM	DATA	UNIT	TEST METHOD
Fabric	100%PES(300D)		DIN EN ISO2060
Total weight	368 (+/-20gsm)	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	150	g/sq.m	DIN53352 BS3424 method5B
Weight of pvc coating	218	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp : 1312	N/5cm	DIN53354 BS3424 method6A
	Weft : 1015		
Tearing strength	Warp : 55	N	DIN53356 BS3424 method 7A
	Weft : 48		
Adhesion	45	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	50	°C	DIN 53372 BS3424 method10
Compatible Printers			Latex, UV, Eco solvent, Solvent
Fire Rating	B1		defined under DIN4102
Lacquering	No		

The indexes above are on average, so there will be ±5% tolerance of actual indexes.

All above information shall only be used as a guide. Buyers shall independently test and determine the products suitability

Graphic Solutions Digital cc

Head Office
4 Midhurst Way
Constantia, 7806

Reg No. CK 1996/003463/23
Vat no. 494 015 4919
Tel: 021 794 6094